

# TEXSTON TEST REPORT

## SCOPE OF WORK

Standard Specification (Plastics – Evaluation of the action of microorganisms (ISO 846:2019)  
Bacterial Growth Test (Method C)

## PRODUCT:

Texston Limestone Cement Plaster  
Texston Slaked Lime Plaster  
Texston Hydraulic Lime Plaster

## REPORT NUMBER

104422759COL-001

## ISSUE DATE

4-February-2021

## PAGES

2

## DOCUMENT CONTROL NUMBER

GFT-OP-10h (6-July-2017)

© 2021 INTERTEK



# MICROBIOLOGICAL PERFORMANCE TEST REPORT

Client		TEXSTON 8025 Deering Avenue Canoga Park, CA 91304
Project No.		G104422759
Sample	Product	Texston Limestone Cement Plaster Texston Slaked Lime Plaster Texston Hydraulic Lime Plaster
	Identification No.	COL2012231511-001
	Date Received	December 23, 2020
	New/Good	New/Good
	Production	Production
Procedural	Engineer	Nicholas Unger
	Reviewer	Lee Moomaw
	Dates Tested	January 01, 2021 – January 29, 2021
	Report Date	February 04, 2021
Standard	Standard Specification (Plastics – Evaluation of the action of microorganisms (ISO 846:2019) Bacterial Growth Test (Method C)	

Method C: Resistance to Bacteria			
Organism Species:	<i>Pseudomonas aeruginosa</i>	ATCC No.:	13388
Incubation Period:	01/08/2021 at 12:00 to 01/29/2021 at 12:00		

Method C: Resistance to Bacteria	
Sample Identifier	Average Growth Rating
Texston Limestone Cement Plaster	No growth
Texston Slaked Lime Plaster	No growth
Texston Hydraulic Lime Plaster	No growth

Test Performed by:



Nicholas Unger  
Staff Engineer  
Columbus Office

Report Approved by:



Lee Moomaw  
Engineering Team Lead  
Columbus Office

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.